




ACOUSTICAL SYSTEMS - LLC

Absorbor™ Panel Random Incidence Performance Data



Chesapeake Acoustic
Research Institute, LLC



FREQ	1" Thick	2" Thick	3" Thick	4" Thick
126	0.14	0.29	0.56	0.76
158	0.16	0.41	0.74	0.88
200	0.20	0.60	0.98	1.04
251	0.24	0.76	1.09	1.12
316	0.35	0.87	1.03	1.03
398	0.50	1.07	1.15	1.12
501	0.69	1.20	1.20	1.14
631	0.83	1.21	1.13	1.14
794	0.95	1.18	1.07	1.13
1000	1.05	1.19	1.08	1.10
1259	1.13	1.18	1.07	1.11
1585	1.10	1.13	1.07	1.11
1995	1.10	1.12	1.07	1.09
2512	1.15	1.15	1.09	1.15
3162	1.07	1.06	1.02	1.08
3981	0.96	0.95	0.93	1.02
5012	0.91	0.91	0.91	1.01