




ACOUSTICAL SYSTEMS - LLC

Absorbor™ Panel Random Incidence Performance Data



FREQ	1"Thick	2" Thick	3"Thick	4"Thick
126	0.14	0.29	0.56	0.76
158	0.16	0.41	0.74	0.88
200	0.20	0.60	0.98	1.04
251	0.24	0.76	1.09	1.12
316	0.35	0.87	1.03	1.03
398	0.50	1.07	1.15	1.12
501	0.69	1.20	1.20	1.14
631	0.83	1.21	1.13	1.14
794	0.95	1.18	1.07	1.13
1000	1.05	1.19	1.08	1.10
1259	1.13	1.18	1.07	1.11
1585	1.10	1.13	1.07	1.11
1995	1.10	1.12	1.07	1.09
2512	1.15	1.15	1.09	1.15
3162	1.07	1.06	1.02	1.08
3981	0.96	0.95	0.93	1.02
NRC	0.77	1.07	1.11	1.11