




ACOUSTICAL SYSTEMS - LLC

Absorbor™ Panel Random Incidence Performance Data



— 1-1/8" Thick — 2-1/8" Thick

Chesapeake Acoustic
Research Institute, LLC



FREQ	1-1/8" Thick	2-1/8" Thick	3-1/8" Thick	4-1/8" Thick
126	0.16	0.32	0.00	0.00
158	0.16	0.42	0.00	0.00
200	0.21	0.62	0.00	0.00
251	0.24	0.74	0.00	0.00
316	0.34	0.84	0.00	0.00
398	0.49	1.04	0.00	0.00
501	0.67	1.17	0.00	0.00
631	0.82	1.19	0.00	0.00
794	0.93	1.16	0.00	0.00
1000	1.04	1.18	0.00	0.00
1259	1.14	1.19	0.00	0.00
1585	1.11	1.14	0.00	0.00
1995	1.13	1.15	0.00	0.00
2512	1.18	1.18	0.00	0.00
3162	1.10	1.09	0.00	0.00
3981	0.99	0.97	0.00	0.00
NRC	0.77	1.06	0.00	0.00